

Norm: UNI EN 1676 e 1706

**Numeric designation:** EN AB and AC - 42100

**Symbolic designation:** EN AB and AC - AISi7Mg0,3

#### CHEMICAL COMPOSITION %

ALLOY DESIGNATION		ELEMENTS												
		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Other each	Other total
EN AB 42100 EN 1676:2020	Min	6,5	0	0	0	0,30	0	0	0	0	0	0	0	0
	Max	7,5	0,15	0,03	0,10	0,45	0,03	0,03	0,07	0,03	0,03	0,18	0,03	0,10
EN AC 42100 EN 1706:2020	Min	6,5	0	0	0	0,25	0	0	0	0	0	0	0	0
	Max	7,5	0,19	0,05	0,10	0,45	0,03	0,03	0,07	0,03	0,03	0,25	0,03	0,10

NOTE: "Other each" includes the limits of all elements unspecified in the grid.

#### MECHANICAL PROPERTIES

(Mechanical properties obtained from samples cast separately at +20°C room temperature)

CASTING PROCESS (condition)	TEMPER DESIGNATION	Rm	Rp02	A	HB	R Fatigue*
		Tensile strength	Yield strength	Elongation	Brinell hardness	Fatigue resistance
		EN 1706:2020	EN 1706:2020	EN 1706:2020	EN 1706:2020	EN 1706:2020
		MPa	MPa	%	HBW	MPa
SAND	T6	230	190	2	75	80 - 110
SAND	T64	200	120	4	60	80 - 110
PERMANENT MOULD	T6	290	210	4	90	80 - 110
PERMANENT MOULD	T64	250	180	8	80	80 - 110
INVESTMENT	T6	260	200	3	75	80 - 110

\*Values for tests under rotating bending conditions up to 10<sup>7</sup> cycles (Wöhler curve)

#### PHYSICAL PROPERTIES

(The following properties are spoilt by the variation of the chemical composition, by its metallurgic structure, casting integrity and casting conditions, therefore these values are approximate)

SPECIFIC WEIGHT	2,66 Kg/dm <sup>3</sup>	ELECTRICAL CONDUCTIVITY	EN 1706:2020	20 - 27 MS/m
SPECIFIC HEAT (at 100 °C)	0,92 J/gK	THERMAL CONDUCTIVITY	EN 1706:2020	160 - 180 W/(m K)
ELASTIC MODULUS	73 GPa	LINEAR THERMAL EXPANSION (20 °C - 100 °C)	EN 1706:2020	22·10 <sup>-6</sup> /K

**Norm:** UNI EN 1676 e 1706

**Numeric designation:** EN AB and AC - 42100

**Symbolic designation:** EN AB and AC - AISi7Mg0,3

## TECHNOLOGICAL FEATURES

(Quality indications excerpted from the norm EN 1706:2020)

<b>CASTABILITY</b>	B	<b>DECORATIVE ANODIZING</b>	D
<b>REASISTANCE TO HOT TEARING</b>	A	<b>ABILITY TO BE WELDED</b>	B
<b>PRESSURE TIGHTNESS</b>	B	<b>ABILITY TO BE POLISHED</b>	C
<b>MACHINABILITY (after cast)</b>	-	<b>STRENGHT AT ROOM TEMPERATURE</b>	A
<b>MACHINABILITY (after heat treatment)</b>	B	<b>STRENGHT AT ELEVATED TEMPERATURE (200°C)</b>	C
<b>RESISTANCE TO CORROSION</b>	B	<b>DUCTILITY</b>	A

**A:** EXCELLENT, **B:** GOOD, **C:** FAIR, **D:** POOR, **E:** NOT RECOMMENDED, **F:** UNSUITABLE

## GUIDELINES FOR USE

The ingot re-melting process must be carried out as fast as possible and overheating must be avoided (maximum melting temperature 760°C). Iron tools that may be touched by the liquid metal must be specially painted to avoid spoiling the alloy. The best alloy purification results are achieved by treating the alloy with inert gases, such as nitrogen and/or argon, to remove dissolved hydrogen and any oxides in the liquid bath. A careful skimming of the bath is recommended. It is allowed to recycle sprues and casting appendages up to 40% out of the total charge weight.

**Heat Treatment** - The possible treatments and the properties to be potentially achieved are listed in the table "MECHANICAL PROPERTIES".

## FURTHER FEATURES OF THE ALLOY

**Resistance to weathering and seawater** - Limited resistance to weathering; not suitable for applications directly touched by seawater.

**Notes** - Castability is excellent and makes it possible to use it a lot. The higher the content of Mg is, the more this alloy tends to hot tearing, even if this tendency is not well-defined. A refining treatment with TiB refiners is recommended to achieve compact components, while a modification treatment with Sodium (Na) or Strontium (Sr) is necessary to increase deformability.

## USUAL APPLICATIONS

A versatile alloy used to produce complex thin-walled, heat-resistant castings. It is used for automotive components, in the building industry and for household appliances.

This alloy **complies (for information)** with Standard **EN 601**.

## DISCLAIMER

Contents are for information purposes only, they do not assure the mentioned properties. The user is held responsible for decisions based on such information and they are not exonerated from verification. Should this not be carried out, Raffmetal S.p.A. assumes no liability.